



# PRODUCT SELECTOR GUIDE

P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS
-----	---------	-------------------------	-------------	--------------	----------	------------	------------------	------------------------

## FUNCTIONAL ADDITIVES

A6220	A-284	93158-39-5 (Y)	Dibutyl-1,4 Cyclohexanedicarboxylate		<ul style="list-style-type: none"> <li>Plasticizer</li> <li>Non-phthalate</li> <li>Very low viscosity</li> </ul>	Colorless Liquid	30	<ul style="list-style-type: none"> <li>For use as a plasticizer in applications where human contact is expected</li> </ul>
R1231	A-304	70293-55-9 (N)	4-Metacryloxyethyl Trimellite Anhydride		<ul style="list-style-type: none"> <li>Adhesion Promoter</li> <li>Versatile adhesion promoter</li> </ul>	White Powder/Crystals	N/A	<ul style="list-style-type: none"> <li>Adhesion promoter</li> </ul>
R1251	A-675-100%	148019-46-9 (Y)	PMGDM		<ul style="list-style-type: none"> <li>Versatile adhesion promoter</li> </ul>	Light Yellow	Very viscous	<ul style="list-style-type: none"> <li>Adhesion promoter</li> </ul>
R1217-M	A-478-M	Not assigned (N)	Pyromellitic Dianhydride Dimethacrylate – Mixture of Isomers		<ul style="list-style-type: none"> <li>Versatile adhesion promoter</li> </ul>	Fine White Powder	N/A	<ul style="list-style-type: none"> <li>Adhesion promoter</li> </ul>
A6165	A-6165	1151654-51-1 (Y)	Soluble additive that on addition to a conductive adhesive formulation can significantly decrease the volume resistivity of the cured material	Unavailable	<ul style="list-style-type: none"> <li>Improves electrical conductivity in metal filled conductive paste formulations</li> <li>Soluble in most resin systems</li> <li>May improve thermal conductivity in some formulations</li> </ul>	Dark Brown Viscous Liquid	**	<ul style="list-style-type: none"> <li>Increases electrical conductivity of resin system</li> </ul>




# PRODUCT SELECTOR GUIDE

P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS
-----	---------	-------------------------	-------------	--------------	----------	------------	------------------	------------------------

## FUNCTIONAL ADDITIVES continued....






A6225	A-6225	No (N)	Antibleed Additive – Silicone Mercapto Propionate (SMP)	Unavailable	<ul style="list-style-type: none"> <li>Excellent bleed control</li> <li>Co-curable in most systems</li> <li>Minimal adhesion degradation</li> <li>Non-halogenated – a 'green' alternative to conventional anti-bleed and mold release materials</li> </ul>	Colorless Liquid	50	<ul style="list-style-type: none"> <li>For use as an additive to reduce resin bleed out specifically on metal surfaces</li> </ul>
-------	--------	--------	---	-------------	--	------------------	----	---

## IMIDE-EXTENDED BISMALEIMIDES

R1155	BMI-689	682800-79-9 (Y-LVE)	A unique very low viscosity BMI resin	 <p>contains unsaturation</p>	<ul style="list-style-type: none"> <li>Toughener</li> <li>Hydrophobic</li> <li>High adhesion *</li> <li>Superior thermal stability</li> </ul>	Yellow to Amber Liquid	1,500 ± 500	<ul style="list-style-type: none"> <li>Base resin or additive in thermoset formulations designed for high temperature resistance</li> </ul>
R1232	BMI-1400	1224691-98-8 (Y)	An amorphous, low molecular weight bismaleimide oligomer that exhibits good adhesion to a variety of substrates	 <p>Where n = 1 to 10</p>	<ul style="list-style-type: none"> <li>Specialty formulated lower viscosity version of BMI-1700</li> </ul>	Amber	6,500 ± 1,000 (60°C)	<ul style="list-style-type: none"> <li>Film adhesives</li> <li>Pre-applied adhesives</li> <li>Adhesion to metal</li> </ul>
R1203	BMI-1500	1290041-56-3 (Y)	An amorphous, low molecular weight bismaleimide oligomer that exhibits good adhesion to a variety of substrates	 <p>Where n = 1 to 10</p>	<ul style="list-style-type: none"> <li>Soluble in many reactive diluents</li> <li>Hydrophobic</li> <li>Superior thermal stability</li> <li>High adhesion to various substrates</li> </ul>	Amber Viscous Liquid	20,000 ± 10,000 (60°C)	<ul style="list-style-type: none"> <li>Film adhesives</li> <li>Pre-applied adhesives</li> <li>Adhesion to metal</li> </ul>

P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS
-----	---------	-------------------------	-------------	--------------	----------	------------	------------------	------------------------


**IMIDE-EXTENDED BISMALEIMIDES continued....**

R1191	BMI-1700	1224691-98-8 (Y)	An amorphous, low molecular weight bismaleimide oligomer that exhibits good adhesion to a variety of substrates	 Where n = 1 to 10	<ul style="list-style-type: none"> <li>• Soluble in many reactive diluents</li> <li>• Hydrophobic</li> <li>• Superior thermal stability</li> <li>• High adhesion to various substrates</li> </ul>	Amber High Viscous Liquid	30,000 ± 10,000 (60°C)	<ul style="list-style-type: none"> <li>• Film adhesives</li> <li>• Pre-applied adhesives</li> <li>• Adhesion to metal</li> </ul>
R1090	BMI-3000 Gel	921213-77-6 (Y)	Bismaleimide oligomer that exhibits excellent flexibility and, on cure, forms very tough hydrophobic polyimides.	 Where n = 1 to 10	<ul style="list-style-type: none"> <li>• Toughener</li> <li>• Hydrophobic</li> <li>• High adhesion *</li> <li>• Superior thermal stability</li> </ul>	Red-Amber Gel	N/A	<ul style="list-style-type: none"> <li>• Film adhesives</li> <li>• Pre-applied adhesives</li> <li>• Adhesion to metal</li> </ul>
R1225	BMI-3000 CG	921213-77-6 (Y)	Low cost bismaleimide oligomer that exhibits excellent flexibility and, on cure, forms very tough hydrophobic polyimides.	 Where n = 1 to 10	<ul style="list-style-type: none"> <li>• Low cost</li> <li>• Toughener</li> <li>• Hydrophobic</li> <li>• High adhesion *</li> <li>• Superior thermal stability</li> </ul>	Light Yellow Powder	N/A	<ul style="list-style-type: none"> <li>• Film adhesives</li> <li>• Pre-applied adhesives</li> <li>• Adhesion to metal</li> </ul>
R1130	BMI-3000 Powder	921213-77-6 (Y)	Bismaleimide oligomer that exhibits excellent flexibility and, on cure, forms very tough hydrophobic polyimides	 Where n = 1 to 10	<ul style="list-style-type: none"> <li>• Toughener</li> <li>• Hydrophobic</li> <li>• High adhesion *</li> <li>• Superior thermal stability</li> </ul>	Light Yellow Powder	N/A	<ul style="list-style-type: none"> <li>• Film adhesives</li> <li>• Pre-applied adhesives</li> <li>• Adhesion to metal</li> </ul>
R1171-P	BMI-5000 Powder	921213-77-6 (Y)	Imide-extended bismaleimide oligomer that exhibits excellent toughness in the cured state with intermediate cross-link density.	 Where n = 1 to 10	<ul style="list-style-type: none"> <li>• Low cross-link density</li> <li>• Non-tacky</li> <li>• Film-forming</li> <li>• Maleimide functional oligomer</li> <li>• Cures to a tough thermoset</li> <li>• Additive to enhance toughness in thermoset compositions</li> </ul>	Light Yellow Powder	N/A	<ul style="list-style-type: none"> <li>• Film adhesives</li> <li>• Thermally resistant adhesives</li> </ul>


# PRODUCT SELECTOR GUIDE


P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS
-----	---------	-------------------------	-------------	--------------	----------	------------	------------------	------------------------

## IMIDE-EXTENDED BISMALEIMIDES continued....

R1171-T	BMI-5000 Toluene	921213-77-6 (Y)	Imide-extended bismaleimide oligomer that exhibits excellent toughness in the cured state with intermediate cross-link density.	 Where n = 1 to 10	<ul style="list-style-type: none"> <li>Low cross-link density</li> <li>Non-tacky</li> <li>Film-forming</li> <li>Maleimide functional oligomer</li> <li>Cures to a tough thermoset</li> <li>Additive to enhance toughness in thermoset compositions</li> </ul>	Dark Brown Liquid	1,000	<ul style="list-style-type: none"> <li>Film adhesives</li> <li>Thermally resistant adhesives</li> </ul>
---------	------------------	-----------------	---	---	---	-------------------	-------	---

## CYCLOSILOXANE EPOXY HYBRIDS



R1163	CS-697	257284-60-9 (Y)	A polyglycidyl ether cyclosiloxane monomer  <b>NOT AVAILABLE IN JAPAN</b>		<ul style="list-style-type: none"> <li>Multifunctional</li> <li>UV curable</li> <li>Low chloride</li> <li>Low viscosity</li> <li>Colorless</li> </ul>	Colorless Liquid	200	<ul style="list-style-type: none"> <li>UV curable additive</li> </ul>
-------	--------	-----------------	---	---	---	------------------	-----	---

R1116	CS-783	921214-21-3 (Y)	Methacrylate epoxy functional hybrid cyclosiloxane monomer		<ul style="list-style-type: none"> <li>Dual cure mechanism</li> <li>Multifunctional</li> <li>UV Curable</li> <li>Low chloride</li> <li>Low viscosity</li> </ul>	Yellow Liquid	250	<ul style="list-style-type: none"> <li>Hybrid cures</li> <li>UV cures</li> <li>B-stageable adhesives</li> </ul>
-------	--------	-----------------	--	--	---	---------------	-----	---

# PRODUCT SELECTOR GUIDE

P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS
-----	---------	-------------------------	-------------	--------------	----------	------------	------------------	------------------------



## PHENYL ESTER EPOXY CURATIVES

R1146	EC-234	926305-16-0 (Y-LVE)	Phenyl ester epoxy curative hybrid		<ul style="list-style-type: none"> <li>Hybrid cure</li> <li>Low viscosity</li> </ul>	Light Yellow Liquid	40	<ul style="list-style-type: none"> <li>UV adhesives</li> <li>B-stageable adhesives</li> </ul>
R1170	EC-298	1044794-71-7 (Y-LVE)	Difunctional phenyl ester epoxy curative		<ul style="list-style-type: none"> <li>Stable</li> <li>Low viscosity</li> <li>Does not impede free radical cure</li> </ul>	Light Yellow Liquid	500	<ul style="list-style-type: none"> <li>Thermoset adhesives</li> <li>Curative for epoxy/(meth) acrylate hybrids</li> <li>Hybrid epoxy/free radical thermosets</li> </ul>
R1227	EC-312	10192-62-8 (Y)	Difunctional phenyl ester epoxy curative		<ul style="list-style-type: none"> <li>Low cost</li> <li>Low melting point</li> <li>Thermal stability</li> <li>Hydrophobic</li> <li>Does not impede free radical cure</li> </ul>	Fine White Powder	N/A	<ul style="list-style-type: none"> <li>Film adhesives</li> <li>Pre-applied adhesives</li> </ul>
R1147	EC-326	N/A (Y-LVE)	Bisphenol A based acetate/proprionate epoxy curative		<ul style="list-style-type: none"> <li>Hydrolytically resistant</li> <li>Low melting point</li> <li>Thermal stability</li> <li>Hydrophobic</li> <li>Toughener</li> <li>Does not impede free radical cure</li> </ul>	White/Yellow Solid	2,000 ***	<ul style="list-style-type: none"> <li>Film adhesives</li> <li>Pre-applied adhesives</li> </ul>
R1148	EC-392	107466-61-9 (Y)	Phenyl ester epoxy curative hybrid of diallyl bisphenol A		<ul style="list-style-type: none"> <li>Dual cure mechanism</li> <li>High cross-link density</li> <li>Multifunctional</li> <li>Thermal stability</li> </ul>	Amber Liquid	2,500	<ul style="list-style-type: none"> <li>B-stageable adhesives</li> <li>Epoxy and BMI co-curable</li> </ul>

# PRODUCT SELECTOR GUIDE

P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS
-----	---------	-------------------------	-------------	--------------	----------	------------	------------------	------------------------

## PHENYL ESTER EPOXY CURATIVES continued....

R1165	EC-861	1071523-12-0 (Y)	Phenyl acetate epoxy curative		<ul style="list-style-type: none"> <li>• Low modulus</li> <li>• Toughener</li> <li>• Hydrolytically resistant thermosets</li> <li>• Hydrophobic</li> <li>• Thermal stability</li> <li>• Does not impede free radical cure</li> </ul>	Amber/Yellow Liquid	2,500	<ul style="list-style-type: none"> <li>• Low stress epoxy thermosets</li> </ul>
R1149	EC-1074	926657-64-9 (Y)	A tetra-phenol epoxy curative derived from dimerdiol		<ul style="list-style-type: none"> <li>• Low modulus</li> <li>• Toughener</li> <li>• Hydrolytically resistant thermosets</li> <li>• Hydrophobic</li> <li>• Thermal stability</li> </ul>	Amber Glassy Solid	N/A	<ul style="list-style-type: none"> <li>• Film Adhesives</li> <li>• Pre-applied adhesive compositions</li> </ul>







## LATENT EPOXY CATALYSTS

R1198 R1207 R1208 R1209	ECAT Series  ECAT-243 ECAT-259 ECAT-353 ECAT-434	1253404-90-8 (Y)	Imidazole Epoxy Catalysts	Unavailable	<ul style="list-style-type: none"> <li>• Good solubility in most epoxy monomers</li> <li>• Excellent latency characteristics</li> <li>• Can be used as a catalyst or curative</li> <li>• Turnable cures</li> <li>• Promotes clean, rapid monomodal cures</li> </ul>	Refer to TDS	N/A	<ul style="list-style-type: none"> <li>• Electronic mold compounds</li> <li>• Underfills</li> </ul>
----------------------------------	---	------------------	---------------------------	-------------	---	--------------	-----	---

# PRODUCT SELECTOR GUIDE

P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS
-----	---------	-------------------------	-------------	--------------	----------	------------	------------------	------------------------




## MONOFUNCTIONAL MONOMERS

R1173	MM-204	33791-58-1 (Y)	Monofunctional acrylate monomer		<ul style="list-style-type: none"> <li>Low viscosity</li> <li>High glass transition temperature</li> <li>Low cure shrinkage</li> <li>Hydrolytically resistant</li> <li>Diluent for thermoset resins</li> <li>High Tg</li> </ul>	Light Tan Liquid	50	<ul style="list-style-type: none"> <li>UV or peroxide cured resins, coatings, or adhesives</li> </ul>
R1175	MM-211	55750-53-3 (Y)	An intermediate chain length, maleimide terminated carboxylic acid		<ul style="list-style-type: none"> <li>Flexible aliphatic backbone</li> <li>Maleimide and carboxylic acid functional groups</li> <li>Adhesion promoter</li> </ul>	White/Light Yellow Powder	N/A	<ul style="list-style-type: none"> <li>Intermediate for ester and amide linked maleimide monomers</li> </ul>
R1139	MM-220	93962-84-6 (Y-LVE)	Tricyclodecane Acrylate		<ul style="list-style-type: none"> <li>Low weight loss on cure</li> <li>Helps reduce cure shrinkage</li> <li>Low viscosity</li> </ul>	Light Yellow Liquid	< 100	<ul style="list-style-type: none"> <li>UV cure coatings</li> </ul>
R1121	MM-281	57079-01-3 (Y-LVE)	Maleimidoundecanoic Acid (MUDA)		<ul style="list-style-type: none"> <li>Flexible aliphatic backbone</li> <li>Maleimide and carboxylic acid functional groups</li> <li>Adhesion promoter</li> </ul>	White to Off-white Powder	N/A	<ul style="list-style-type: none"> <li>Intermediate for ester and amide linked maleimide monomers</li> </ul>
R1134	MM-290	903876-45-9 (Y)	Isobornyl Cyclohexyl Acrylate		<ul style="list-style-type: none"> <li>Lower weight loss on cure than Isobornyl Acrylate (IBOA)</li> <li>Mild, pleasant odor</li> <li>Hydrolytic resistance</li> </ul>	Light Tan Liquid	250	<ul style="list-style-type: none"> <li>UV or peroxide cured resins, coatings, or adhesives</li> </ul>
R1197	MM-304	N/A (N)	Isobornyl Cyclohexyl Methacrylate		<ul style="list-style-type: none"> <li>Very low color</li> <li>Lower weight loss on cure than Isobornyl Methacrylate (IBOMA)</li> <li>Mild, pleasant odor</li> <li>Hydrolytic resistance</li> </ul>	Colorless Liquid	80	<ul style="list-style-type: none"> <li>Dental</li> <li>Reactive diluent</li> </ul>

# PRODUCT SELECTOR GUIDE



P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS
-----	---------	-------------------------	-------------	--------------	----------	------------	------------------	------------------------

## POLYESTER ACRYLATE METHACRYLATES

R1096	PEAM-645	921213-39-0 (Y)	Polyester acrylate/methacrylate	 Where n = 1 to 5	<ul style="list-style-type: none"> <li>• High Tg</li> <li>• High modulus</li> <li>• Low CTE</li> <li>• High adhesion I</li> <li>• Thermal stability</li> </ul>	Amber Liquid	6,500	<ul style="list-style-type: none"> <li>• Low CTE thermosets</li> </ul>
R1111	PEAM-1044	921214-61-1 (Y)	Polyester acrylate/methacrylate	 Where n = 1 to 5	<ul style="list-style-type: none"> <li>• Low warpage</li> <li>• Hydrophobic</li> <li>• High adhesion *</li> <li>• Thermal stability</li> </ul>	Amber Liquid	(40°C)	<ul style="list-style-type: none"> <li>• Low stress coatings</li> </ul>
R1144	PEAM-1769	921214-61-1 (Y)	Polyester acrylate/methacrylate	 Where n = 1 to 5	<ul style="list-style-type: none"> <li>• Ultra-low modulus</li> <li>• Hydrophobic</li> <li>• High adhesion *</li> <li>• High thermal stability</li> <li>• Adhesion to metals</li> <li>• Flexibilizer</li> </ul>	Amber Liquid	4,500	<ul style="list-style-type: none"> <li>• Low stress coatings</li> </ul>

# PRODUCT SELECTOR GUIDE




P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS
-----	---------	-------------------------	-------------	--------------	----------	------------	------------------	------------------------

POLYESTER METHACRYLATES								
R1188	PEM-665	N/A (N)	Methacrylate terminated polyester oligomer		<ul style="list-style-type: none"> <li>Low color</li> <li>Low cure shrinkage</li> <li>Thermal stability</li> <li>Tough</li> </ul>	Light Yellow Tint Liquid	6,500 (50°C)	• Dental
R1157	PEM-1066	951244-55-6 (Y-LVE)	Polyester methacrylate		<ul style="list-style-type: none"> <li>Low modulus</li> <li>Hydrophobic</li> <li>Excellent hydrolytic resistance</li> <li>High adhesion *</li> <li>Adhesion to metals</li> <li>Ultra-low warpage</li> <li>Flexibilizer</li> </ul>	Light Yellow Liquid	20,000	<ul style="list-style-type: none"> <li>Dental</li> <li>Moisture resistant coatings</li> </ul>

# PRODUCT SELECTOR GUIDE

P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS
-----	---------	-------------------------	-------------	--------------	----------	------------	------------------	------------------------

## FUNCTIONAL URETHANES

R1216	U-347	1371570-15-8 (N)	Phenyl glycerol urethane dimethacrylate (PGDMA)		<ul style="list-style-type: none"> <li>Low cure shrinkage</li> <li>Colorless</li> <li>Good refractive index</li> <li>Not bisphenol A based</li> </ul>	Clear Colorless Liquid	9,500	<ul style="list-style-type: none"> <li>Dental</li> <li>Moisture resistant coatings</li> </ul>
R1230	U-483	Not assigned (N)	IPDI urethane dimethacrylate		<ul style="list-style-type: none"> <li>Low viscosity</li> <li>Low cure shrinkage</li> <li>Colorless</li> <li>Not bisphenol A based</li> </ul>	Clear Colorless Liquid	5,000	<ul style="list-style-type: none"> <li>Dental</li> <li>Moisture resistant coatings</li> <li>Light cure coatings</li> </ul>
R1095	U-793	869488-57-3 920758-62-9 902742-80-9 (Y)	Urethane resin functionalized with a methacrylate and an epoxy	Unavailable	<ul style="list-style-type: none"> <li>Low color</li> <li>Low cure shrinkage</li> <li>Thermal stability</li> <li>Tough</li> </ul>	Light Yellow Tint Liquid	6,500 (50°C)	<ul style="list-style-type: none"> <li>Dental</li> </ul>
R1102	U-835	869488-57-3 1003557-45-6 1003612-76-7 (Y-LVE)	Urethane resin functionalized with acrylate and methacrylate end groups	Unavailable	<ul style="list-style-type: none"> <li>Low modulus</li> <li>Hydrophobic</li> <li>Excellent hydrolytic resistance</li> <li>High adhesion *</li> <li>Adhesion to metals</li> <li>Flexibilizer</li> </ul>	Light Yellow Liquid	20,000	<ul style="list-style-type: none"> <li>Dental</li> <li>Moisture resistant coatings</li> </ul>
R1238	U-847	86499-57-3 (N)	DDI urethane dimethacrylate monomer		<ul style="list-style-type: none"> <li>Low modulus</li> <li>Low color</li> <li>Low cure shrinkage</li> <li>Hydrophobic</li> <li>Flexibilizer</li> </ul>	Light Yellow Liquid	2,500	<ul style="list-style-type: none"> <li>Dental</li> <li>Moisture resistant coatings</li> </ul>



# PRODUCT SELECTOR GUIDE

P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS
-----	---------	-------------------------	-------------	--------------	----------	------------	------------------	------------------------

## FUNCTIONAL URETHANES continued....

R1228	U-471	72869-86-4 (Y)	TMDI urethane dimethacrylate monomer	<p>The structure shows two molecules of trimellitic anhydride (TMDI) reacting with a diamine. The resulting product is a urethane-linked polymer chain containing methacryloyl groups (-CH<sub>2</sub>=CH-C(=O)-CH<sub>2</sub>-) at the ends.</p>	<ul style="list-style-type: none"> <li>Low color</li> <li>Low cure shrinkage</li> </ul>	Slight Yellow Liquid	8,000	<ul style="list-style-type: none"> <li>Dental</li> </ul>
R1266	U-443	TBD (N)	TMDI urethane diacrylate monomer	<p>The structure shows two molecules of trimellitic anhydride (TMDI) reacting with a diamine. The resulting product is a urethane-linked polymer chain containing acryloyl groups (-CH<sub>2</sub>=CH-C(=O)-CH<sub>2</sub>-) at the ends.</p>	<ul style="list-style-type: none"> <li>Excellent Curing Properties</li> </ul>	Clear, Colorless, Oil	5,500	<ul style="list-style-type: none"> <li>Light-cured coating resins</li> </ul>

## FORMULATED PRODUCTS

R1267	DMI-2550	Mixture (Y)	A BMI-based coating for dispense applications	Mixture	<ul style="list-style-type: none"> <li>Low modulus</li> <li>Hydrophobic</li> <li>Excellent hydrolytic resistance</li> <li>Low stress</li> <li>Adhesion to metals</li> <li>Flexibilizer</li> </ul>	Yellow to Dark Amber Liquid	700 ± 100	<ul style="list-style-type: none"> <li>Die top coating applications</li> </ul>
R1246	DMI-3005	Mixture (Y)	Unique class leading coating	Mixture	<ul style="list-style-type: none"> <li>Low modulus</li> <li>Hydrophobic</li> <li>Low stress</li> <li>Low cure shrinkage</li> <li>Adhesion to metals</li> </ul>	Yellow Liquid	250	<ul style="list-style-type: none"> <li>Wafer buffer coating RDL</li> </ul>

ALL DATA PROVIDED FOR REFERENCE ONLY AND MAY VARY BY TEST METHOD

\* Various substrates

\*\* Many of the structures are an idealized representation of a statistical distribution

\*\*\* Supercooled

\*\*\*\* Storage at < 25°C will result in precipitation of some solids. The fully liquid state can be regenerated by warming to 40°C until all solids dissolve

LVE

Material manufactured under Low Volume Exemption (LVE) in compliance with Section 5(h)(4) of the Toxic Substances Control Act (TSCA), 15 U.S.C.

TO PLACE AN ORDER, REQUEST SAMPLES, OR TO SPEAK WITH US ABOUT DEVELOPING A PRODUCT FOR YOUR CHEMICAL NEEDS, CONTACT US AT 858-348-1122.